

| | | Grade Selection | | | | | | | | | | | |
|-----------------|---|--|-------|-------|-------|-------|-------|--|-------|-------|-------|-------|-------|
| | | MIRAPAINT X Line - Mixed Class Additives | | | | | | MIRAPAINT C Line - Clear Class Additives | | | | | |
| Product Names | | X-4 | X-6 | X-9 | X-12 | X-22 | X-40 | C-4 | C-6 | C-9 | C-12 | C-22 | C-40 |
| Properties | D50 (median µm) | 4 | 6 | 9 | 12 | 22 | 40 | 4 | 6 | 9 | 12 | 22 | 40 |
| | D97 (µm) | ≤ 21 | ≤ 30 | ≤ 50 | ≤ 60 | ≤ 110 | ≤ 350 | ≤ 21 | ≤ 30 | ≤ 50 | ≤ 60 | ≤ 110 | ≤ 350 |
| | Bulk Density (g / cm3) | 0.88 | 0.92 | 1 | 1 | 1.1 | 1.25 | 0.88 | 0.92 | 1 | 1 | 1.1 | 1.25 |
| | Oil Absorption (ASTM D281) | 37 | 36 | 34 | 31 | 28 | 26 | 37 | 36 | 34 | 31 | 28 | 26 |
| | Specific Surface (m2 / kg) | > 650 | > 600 | > 550 | > 400 | > 300 | > 250 | > 650 | > 600 | > 550 | > 400 | > 300 | > 250 |
| Applications | Adhesives | ○ | ○ | ● | ● | ● | ● | ○ | ○ | ○ | ○ | ○ | ○ |
| | Asphalt Cutback Roof Coatings | | ● | ● | ● | ● | ● | | ○ | ○ | ○ | ○ | ○ |
| | Asphalt Patching Compounds | | ● | ● | ● | ● | ● | | ○ | ○ | ○ | ○ | ○ |
| | EIFS | ● | ● | ● | ● | ● | ● | ○ | ○ | ○ | ○ | ○ | ○ |
| | Elastomers Coatings | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| | Joint Compounds | ● | ● | ● | ○ | ○ | | ● | ● | ● | ○ | ○ | |
| | White or Pale Interior/ Exterior Coatings | ○ | ○ | ○ | ○ | | | ● | ● | ● | ● | | |
| | Pale Color Sealants | | ○ | ○ | ○ | ○ | | | ● | ● | ● | ● | |
| | Medium to Dark Interior/ Exterior Coating | ● | ● | ● | ● | | | ○ | ○ | ○ | ○ | | |
| | Dark Color Sealants | | ● | ● | ● | ● | | | ○ | ○ | ○ | ○ | |
| | Mastics and Putties | ○ | ○ | ● | ● | ● | ● | ○ | ○ | ● | ● | ● | ● |
| | Primers | | | | ● | | | ○ | ○ | ○ | ○ | | |
| | Epoxy | ● | ● | ● | ○ | ○ | ○ | ● | ● | ● | ○ | ○ | ○ |
| | Industrial Finishes | ● | ● | ● | ● | ○ | ○ | ● | ● | ● | ● | ○ | ○ |
| ○ Could Be Used | | ● Recommended | | | | | | | | | | | |